








TEST PROCEDURE - CHASE (SAE - J661a)

FRICITION



TEST NR: 21.816/04
 DATE: 25/03/04
 QUALITY: NASC 100/B
 BATCH: D4C
 REFERENCE: -----

	RESULTS	SPECIFIC.
μ NORMAL	0,384	0,350 - 0,490
μ HOT	0,385	0,350 - 0,490
CLASS	FF	-----
WEAR (mm)	0,360	M&x. 0,370
WEAR (gr)	0,514	M&x. 0,530

APPROVED - Q.C.
 REJECTED - Q.C.
 DEVELOPMENT

Rebel
 ELABORATED
 APPROVED